BASWA Fine

2026/1

Product description and areas of application

The ready-to-use, high quality and open pore BASWA Fine coating substance is manufactured from natural marble sand. BASWA Fine is processed as a final coating for the BASWA System Fine.

Product data

Product base	Synthetic resin plaster containing marble sand, water based (solvent-free)
Item number	a006
Grain size	0.5 mm
Standard colour	White ~ NCS S 0500-N
Other colours	RAL/NCS
Storage	Protect from frost, keep only in original packing Storge-/transport temperature between +5°C and +30°C Protect from direct sunlight Store in a dry place on pallets Can be stored up to 12 months under optimal conditions

BASWA acoustic AG Marmorweg 10 CH-6283 Baldegg T +41 (0)41 914 02 22 info@baswa.com **www.baswa.com**

Delivery

Delivered as	Container of 25 kg

For further information about delivery, please contact BASWA acoustic AG, T +41 (0)41 914 02 22.

Application regulations

Processing

BASWA Fine

One-coat system

Intended Use	**Fine as final coating** (one coat)
Applied using a notched trowel	6 x 6 mm notches
Consumption kg/m²	3.5–4.0
Approx. processing time	10–15 Min./m²
Drying time at 20°C/50% π	~ 48 Hrs.

Processing methods
Manual application or with machine (special spraying machines required – Info from BASWA acoustic).
Bonding characteristics
Air drying. When completely dry (<10% moisture) practically insoluble in water.
Processing conditions
More than 15°C during processing until completely dry (<10% moisture), no temperature deviations >5°/prevent falls in temperature! Processing <30°C/>15°C. Prevent quick drying through air circulation or draught.
Processing note
Fundamentally, our general applicable BASWA processing directives must be observed.

BASWA Classic

Intended Use	**Fine as final coating** (based on an overcoat)
Applied using a notched trowel	3 x 3 mm notches
Consumption kg/m²	2.5–3.0
Approx. processing time	10–15 Min./m²
Drying time at 20°C/50% π	~ 36 Hrs.

Processing methods
Manual application or with machine (special spraying machines required – Info from BASWA acoustic).
Bonding characteristics
Air drying. When completely dry (<10% moisture) practically insoluble in water.

Processing conditions
More than 15°C during processing until completely dry (<10% moisture), no temperature deviations >5°/prevent falls in temperature! Processing <30°C/>15°C. Prevent quick drying through air circulation or draught.
Processing note
Fundamentally, our general applicable BASWA processing directives must be observed.

For further information about safety during transportation, storage and handling, as well as disposal, refer to the BASWA safety data sheet (www.baswa.com).

Disclaimer

The previously mentioned data, in particular the suggestions for the processing and application of our products, are based on our knowledge and experience in the normal case, prerequisite is that the products have been correctly stored and used. Because of the different materials, surfaces and deviating working conditions, no guarantee of the result of the work can be given, or liability be placed, regardless of the legal relationship, neither from these instructions, nor from verbal advice, unless we are culpable of intent or gross negligence. Hereby, the user must prove that he/she has provided punctual, complete written knowledge to BASWA in order for BASWA to attain a correct and successful evaluation. Upon receipt, the user must check the products for their suitability for the envisaged application. Changes to the product specifications remained reserved. Observe the protection rights of third parties. Furthermore, our respective sales and delivery conditions remain applicable. The current product data sheet is applicable and can be requested from us.